

NORBOOK SUPER

PRODUCT SPECIFICATION

BASIC PROPERTIES

| | | |
|------------------------|-----|----|
| Basic Weight (nominal) | gsm | 70 |
| Moisture Content | % | 8 |

STRUCTURAL PROPERTIES

| | | |
|-----------|-----|-----|
| Caliper | µm | 141 |
| Roughness | µm> | 5.5 |

OPTICAL PROPERTIES

| | | |
|---------------|------|------|
| Brightness | ISO | 68.9 |
| Opacity (min) | % | 91.0 |
| L* | unit | 91.4 |
| a* | unit | -0.9 |
| b* | unit | 9.9 |

MECHANICAL PROPERTIES

| | | |
|-------------------|------|-----|
| Tear index, CMD | mN | 650 |
| Tensile index, MD | kN/m | 3.4 |
| Stretch, MD | % | 1.2 |

Note: (1) Values shown are typical values; normal operational variances occur(2) Shade controlled to L*, a*, b*, ISO approximate

PRODUCTION DATA

Mill of supply

Boyer

Roll width range:

300mm - 2060mm

Diameters (mm)

1015 - 1250

Core size

76mm (Inner)

ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

CERTIFICATION

- Certification ISO14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody



For more information & samples, please contact your Norske Skog Account Team on:

AU: +61 2 8268 2000

NZ: +64 9 524 3400

Email: reception.sydney@norskeskog.com