

NORBRIGHT

PRODUCT SPECIFICATION

BASIC PROPERTIES

Basic Weight (nominal)	gsm	48.8	52
Moisture Content	%	8.8	8.8

STRUCTURAL PROPERTIES

Caliper	µm	78	82
Roughness	µm	3.5	3.5

OPTICAL PROPERTIES

Brightness	ISO	70	70
Opacity (min)	%	90.3	91.3
L*	unit	87.5	87.5
a*	unit	-0.1	-0.1
b*	unit	3.65	3.65

MECHANICAL PROPERTIES

Tear index, CMD	mN	350	390
Tensile index, MD	kN/m	2.4	2.45
Stretch, MD	%	1.1	1.1

Note: (1) Values shown are typical values; normal operational variances occur(2) Shade controlled to L*, a*, b*, ISO approximate

PRODUCTION DATA

Mill of supply

Boyer & Tasman

Roll width range:

300mm - 2060mm

Diameters (mm)

1015, 1265

Core size

76mm (Inner)

ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

CERTIFICATION

- Certification ISO14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody



For more information & samples, please contact your Norske Skog Account Team on:

AU: +61 2 8268 2000

NZ: +64 9 524 3400

Email: reception.sydney@norskeskog.com