

## BASIC PROPERTIES

Basic Weight (nominal)	gsm	42	45	48.8
Moisture Content	%	9.2	9.2	9.2

## STRUCTURAL PROPERTIES

Caliper	µm	68	72	77
Roughness (max)	µm	3.3	3.3	3.3

## OPTICAL PROPERTIES

Opacity (min)	%	93.0	93.5	94.5
L*	unit	79.2	79.2	79.2
a*	unit	0.0	0.0	0.0
b*	unit	1.4	1.4	1.4

## MECHANICAL PROPERTIES

Tear index, CMD	mN	300	310	340
Tensile index, MD	kN/m	2.3	2.4	2.4
Stretch, MD	%	1.1	1.1	1.1

**Note:** (1) Values shown are typical target values; normal operational variances occur  
 (2) Caliper shown is Boyer and Tasman. Albury caliper 2-3 points higher  
 (3) Shade targets are Boyer. Tasman and Albury visual match to Boyer, controlled to L\*a\*b\*, ISO approximate  
 (4) Moisture measured by ABB is approx. 1 point lower

## PRODUCTION DATA

### Mill of supply

Albury, Boyer & Tasman

### Roll width range:

300mm - 2060mm

### Diameters (mm)

1015, 1265

### Core size

76mm (Inner)

## ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

## CERTIFICATION

- Certification ISO14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody



For more information & samples, please contact your Norske Skog Account Team on:

AU: +61 2 8268 2000

NZ: +64 9 524 3400

Email: reception.sydney@norskeskog.com