

### BASIC PROPERTIES

Basic Weight (nominal)	gsm	52	55
Moisture Content	%	8.8	8.8

### STRUCTURAL PROPERTIES

Caliper	µm	81	86
Roughness	µm	3.4	3.5

### OPTICAL PROPERTIES

Brightness	ISO	74	74
Opacity (min)	%	90.3	91.3
L*	unit	90	90
a*	unit	0.0	0.0
b*	unit	3.45	3.45

### MECHANICAL PROPERTIES

Tear index, CMD	mN	380	420
Tensile index, MD	kN/m	2.4	2.45
Stretch, MD	%	1.1	1.15

**Note:** (1) Values shown are typical values; normal operational variances occur(2) Shade controlled to L\*, a\*, b\*, ISO approximate

### PRODUCTION DATA

**Mill of supply**

Boyer

**Roll width range:**

300mm - 2060mm

**Diameters (mm)**

1015 - 1250

**Core size**

76mm (Inner)

### ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

### CERTIFICATION

- Certification ISO14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody



**For more information & samples, please contact your Norske Skog Account Team on:**

AU: +61 2 8268 2000

NZ: +64 9 524 3400

Email: [reception.sydney@norskeskog.com](mailto:reception.sydney@norskeskog.com)