

BASIC PROPERTIES

Basic Weight (nominal)	gsm	51	54	57	60	65
------------------------	-----	----	----	----	----	----

STRUCTURAL PROPERTIES

Caliper	µm	52	54	56	58	61
Bulk	cm ³ /g	1.02	1.0	0.98	0.96	0.94

OPTICAL PROPERTIES

Brightness	ISO	73	73	73	73	73
Gloss (Hunter)	%	43	43	45	45	45
Opacity	%	91	92	93	94	95
L*	unit	87.5	87.5	87.5	87.5	87.5
a*	unit	0.2	0.2	0.2	0.2	0.2
b*	unit	-0.5	-0.5	-0.5	-0.5	-0.5

Note: (1) Values shown are typical values; normal operational variances occur (2) Shade controlled to L*, a*, b*, ISO approximate

PRODUCTION DATA

Mill of supply

Boyer, Tasmania

Roll width range

300mm - 2060mm

Diameters (mm)

1015 - 1250

Core size

76mm (ID), 106mm (OD)

ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

CERTIFICATION

- Certification ISO14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody



For more information & samples, please contact your Norske Skog Account Team on:
 AU: +61 2 8268 2000
 NZ: +64 9 524 3400
 Email: vantage@norskeskog.com